CORE-15

CLEAR GLOSS PCU PAINT PROTECTION FILM

PRODUCT CODE C15-75 / NOMINAL 7.5 MIL / CLEAR GLOSS FINISH

Core-15 is Sentrix's flagship transparent gloss PCU paint protection film, built on advanced Covestro PCDL chemistry for outstanding mechanical performance, durable adhesion, high optical clarity and heat-assisted surface recovery. It is intended for professional installation on compatible automotive paintwork, including ceramic-coated surfaces.

7.5 MIL	135 GU	90%	15 YEARS
NOMINAL THICKNESS	GLOSS @ 60 DEG	LIGHT TRANSMITTANCE	LIMITED WARRANTY*

PRODUCT CONSTRUCTION

01	02	03	04	05
TOP PROTECTIVE PET 46 µm removable carrier	**HYDROPHOBIC TOP COAT** Integrated coating / 20 µm	**COVESTRO PCDL PCU CORE** Advanced transparent base film	**ADHESIVE** Ashland AROSET™ 951059 / 30 µm	**RELEASE PET** 75 µm removable liner

PRODUCT SPECIFICATIONS

PARAMETER	SPECIFICATION
Product type	Clear gloss PCU paint protection film
Nominal thickness	7.5 mil (finished film tested at 190 µm)
Base material	Covestro PCDL-based PCU
Top coat	Integrated hydrophobic coating
Top-coat thickness	20 µm
Adhesive	Ashland AROSET™ 951059 pressure-sensitive adhesive
Adhesive layer	30 µm
Colour / appearance	Colourless, transparent, flat and uniform
Suitable paintwork	Compatible automotive surfaces, including ceramic-coated paintwork
Roll dimensions	1.52 m x 15 m
Sentrix limited warranty	15 years*

OPTICAL AND SURFACE PERFORMANCE

PROPERTY	TEST METHOD	REQUIREMENT	RESULT
Surface gloss	Gloss meter @ 60°	>=95 GU	135 GU
Light transmittance	Float-glass method	>=90%	90%
PCU haze	Haze meter	<=3%	0.96%
UV blocking	LS182 tester	>90%	97%
Hydrophobicity	Marker-pen line test	Hydrophobic	Confirmed
Stain resistance	Marker residue after alcohol wipe	Score 0-10	8 / 10

PERFORMANCE TEST RESULTS

MECHANICAL, DURABILITY AND QUALITY CONTROL

Production COA reference: SSR 7.5mil / test date 3 May 2026

MECHANICAL PERFORMANCE

PROPERTY	TEST METHOD	REQUIREMENT	RESULT
Elongation at break	PT-6081G	>=150%	403%
Tensile strength	PT-6081G	>15 MPa	17.7 MPa
100% modulus	PT-6081G	>6 MPa	7.5 MPa
Tearing strength	GB/T 529	>=40 kN/m	95.3 kN/m
Adhesive peel - 20 min	GB/T 2792-2014	>1,400 gf	2,252 gf

DURABILITY PERFORMANCE

PROPERTY	TEST CONDITION	REQUIREMENT	RESULT
QUV ageing resistance	ASTM G154-16, Cycle 1, 1,000 h	ΔE*ab <2	0.15
Heat self-healing	Scratch recovery using 70°C hot water or hot air	100% self-healing	100%
Scratch resistance	1,000 copper-brush cycles at 500 g	No damage after thermal repair	No damage
Temperature resistance	80 ±2°C for 24 h; recover 2 h; then -20 ±2°C for 24 h	No cracks, turbidity, bubbles or discoloration	No abnormality

APPEARANCE QUALITY CONTROL

PROPERTY	METHOD	ACCEPTANCE CRITERIA	RESULT
Visual colour	Visual inspection	Colourless and transparent	Qualified
Product appearance	Visual inspection	No impurities, coating lines, bubbles, tension marks or water ripples	Qualified
Crystal / impurity points	Visual inspection	0.6-1.0 mm: <=6 pcs/m2; >1.0 mm: 0	Qualified

Application: Professional automotive installation only. Confirm substrate condition and paint compatibility before application. Use approved installation solution, tools and edge-finishing practices.
Thickness: The tested finished-film thickness of 190 µm is the sum of PCU, coating and adhesive layers. Removable PET carriers are excluded.
Data basis: Values are based on the cited production certificate and may vary within normal manufacturing tolerances. This sheet is not a substitute for installation or warranty terms.
*Warranty: Fifteen-year Sentrix limited warranty, subject to registration, approved installation, care requirements, exclusions and the prevailing Sentrix warranty policy.